

Name	Nick name	Application	Density	MFI (g/10 min)
(g/cm3)	2.16	5	21.6	-
LLDPE				
LL-22501	(AA-K)	Film	0.922	0.95
HDPE				
HM-8355 (HD)	BL4	Blow molding (>5 ltr)	0.951	0.35
HD-60507/UV	-	injection	0.958	7.5
HD-60505	-	injection	0.957	5.5
HD-52518	-	injection	0.952	18
HF-4760	BL3	Blow molding (<5 ltr)	0.954	1.2
HM9450F	EX5	Film	0.949	0.28
HD-52511	-	injection	0.952	11
HD-52505/UV	-	injection	0.952	5
Extrusion				
HM CRP 100 (HD)	PE 100	pipe	0.955-0.960	0.22
HM-5010TZN (HD)	EX3 (PE80)	pipe	0.945	0.45
Rotomolding				
LL32604/UV (LLD)	-	Roto	0.932	4
MD 38504 UV	-	Roto	0.938	4